

Slag, CRM, Steelmaking Slag, Powder

Art. ID NH-143
Unit 75 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al ₂ O ₃		~0,5	%		
	CaO		42,9	%		
	Cr ₂ O ₃		0,97	%		
	Iron (Fe)	[7439-89-6]	14,53	%		
	FeO		8,62	%		
	MgO	[1309-48-4]	5,29	%		
	MnO		2,84	%		
	P ₂ O ₅		16,71	%		
	Sulfur (S)	[7704-34-9]	0,083	%		
	SiO ₂		4,88	%		
	TiO ₂		0,15	%		