

Slag, CRM, Steelmaking Slag, Powder

Art. ID NH-145
Unit 75 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al ₂ O ₃		2,39	%		
	CaO		20,85	%		
	Cr ₂ O ₃		0,99	%		
	Iron (Fe)	[7439-89-6]	27,97	%		
	FeO		30,46	%		
	MgO	[1309-48-4]	2,71	%		
	MnO		9,26	%		
	P ₂ O ₅		2,05	%		
	Sulfur (S)	[7704-34-9]	0,089	%		
	SiO ₂		22,43	%		
	TiO ₂		0,56	%		