

***** last unit*** Slag, CRM, Steelmaking Slag, Powder**

Art. ID NH-149
Unit 75 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al ₂ O ₃		3,36	%		
	CaO		9,85	%		
	Cr ₂ O ₃		53,81	%		
	Iron (Fe)	[7439-89-6]	14,09	%		
	FeO		8,12	%		
	MgO	[1309-48-4]	2,89	%		
	MnO		3,74	%		
	P ₂ O ₅		-0,03	%		
	Sulfur (S)	[7704-34-9]	0,04	%		
	SiO ₂		8,42	%		
	TiO ₂		0,22	%		