

Slag, CRM, Steelmaking Slag, Powder

Art. ID NH-150
Unit 75 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al ₂ O ₃		3,23	%		
	CaO		21,77	%		
	Cr ₂ O ₃		1,74	%		
	Iron (Fe)	[7439-89-6]	24,23	%		
	FeO		27,3	%		
	MgO	[1309-48-4]	~14,46	%		
	MnO		8,16	%		
	P ₂ O ₅		0,62	%		
	Sulfur (S)	[7704-34-9]	0,044	%		
	SiO ₂		15,69	%		
	TiO ₂		0,15	%		