

Slag, CRM, Steelmaking Slag, Powder

Art. ID NH-151
Unit 75 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al ₂ O ₃		2,06	%		
	CaO		34,83	%		
	Cr ₂ O ₃		0,65	%		
	Iron (Fe)	[7439-89-6]	14,94	%		
	FeO		0,14	%		
	MgO	[1309-48-4]	5,05	%		
	MnO		8,44	%		
	P ₂ O ₅		7,92	%		
	Sulfur (S)	[7704-34-9]	0,079	%		
	SiO ₂		15,97	%		
	TiO ₂		0,53	%		