

Slag, CRM, Steelmaking Slag, Powder

Art. ID NH-152
Unit 75 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al ₂ O ₃		2,6	%		
	CaO		21,95	%		
	Cr ₂ O ₃		28,67	%		
	Iron (Fe)	[7439-89-6]	14,4	%		
	FeO		12,79	%		
	MgO	[1309-48-4]	6,17	%		
	MnO		4,85	%		
	P ₂ O ₅		~0,12	%		
	Sulfur (S)	[7704-34-9]	0,028	%		
	SiO ₂		15,91	%		
	TiO ₂		0,37	%		