

Slag, CRM, Steelmaking Slag, Powder

Art. ID NH-154
Unit 75 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al ₂ O ₃		3,68	%		
	CaO		~1,15	%		
	Cr ₂ O ₃		1,54	%		
	Iron (Fe)	[7439-89-6]	10,65	%		
	FeO		13,36	%		
	MgO	[1309-48-4]	2,44	%		
	MnO		~28	%		
	P ₂ O ₅		~0,03	%		
	Sulfur (S)	[7704-34-9]	0,074	%		
	SiO ₂		48,67	%		
	TiO ₂		0,27	%		