

Slag, CRM, Ironmaking Slag (M14), Powder

Art. ID NH-7-1-008
Unit 75 g (powder)
Deliverydetails No Dangerous Good /not restricted

| Text/Information | Analyte/Parameter | CAS number | Concentration/Value | Unit | Method | Source |
|------------------|--------------------------------|-------------|---------------------|------|--------|--------|
| | Al ₂ O ₃ | | 8,4 | % | | |
| | CaO | | 42,1 | % | | |
| | Iron (Fe) | [7439-89-6] | 0,3 | % | | |
| | K ₂ O | | ~0,52 | % | | |
| | MgO | [1309-48-4] | 6,1 | % | | |
| | MnO | | 0,73 | % | | |
| | Na ₂ O | | ~0,33 | % | | |
| | Sulfur (S) | [7704-34-9] | ~0,65 | % | | |
| | SiO ₂ | | 39,1 | % | | |
| | TiO ₂ | | 0,3 | % | | |