

Layer Thickness, CRM, 6 layers of GaAs and AlAs: (9.24), 9.65, 9.51, 9.64, 9.51, 9.62, Plate 15 mm x 15 mm x 1 mm

Art. ID NMIJ-5203a
Unit plate
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Surface oxide		~ 1.32			
	First layer (GaAs)		~ 9.24			
	Second layer (AlAs)		9.65			
	Third layer (GaAs)		9.51			
	Fourth layer (AlAs)		9.64			
	Fifth layer (GaAs)		9.51			
	Sixth layer (AlAs)		9.62			