

Cement, RM, Portland Cement, Powder

Art. ID TL-200Ca
Unit 40 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		~3,3	%		
	Insoluble Residue		~17,42	%		
	Al ₂ O ₃		8,72	%		
	CaO		49,97	%		
	Free CaO		~0,34	%		
	Fe ₂ O ₃		4,07	%		
	K ₂ O		1,1	%		
	MgO	[1309-48-4]	2,06	%		
	Na ₂ O		0,21	%		
	P ₂ O ₅		0,45	%		
	SO ₃		2,84	%		
	SiO ₂		26,55	%		
	SrO		0,13	%		
	TiO ₂		0,46	%		