

## **Fused Welding Flux, CRM, Powder**

Art. ID VS-SH7/3  
Unit 100 g (powder)  
Deliverydetails No Dangerous Good /not restricted

| Text/Information | Analyte/Parameter              | CAS number  | Concentration/Value | Unit | Method | Source |
|------------------|--------------------------------|-------------|---------------------|------|--------|--------|
|                  | Al <sub>2</sub> O <sub>3</sub> |             | 29,8 ± 0,1          | %    |        |        |
|                  | CaF <sub>2</sub>               |             | 28,5 241 0,1        | %    |        |        |
|                  | CaO                            |             | 24 ± 0,1            | %    |        |        |
|                  | Fe <sub>2</sub> O <sub>3</sub> |             | 0,56 ± 0,01         | %    |        |        |
|                  | K <sub>2</sub> O               |             | 0,94 241 0,02       | %    |        |        |
|                  | MgO                            | [1309-48-4] | 11,4 ± 0,1          | %    |        |        |
|                  | MnO                            |             | 0,4 ± 0,01          | %    |        |        |
|                  | Na <sub>2</sub> O              |             | 1,41 ± 0,03         | %    |        |        |
|                  | Phosphorus (P)                 | [7723-14-0] | 0,011 ± 0,001       | %    |        |        |
|                  | Sulfur (S)                     | [7704-34-9] | 0,031 ± 0,001       | %    |        |        |
|                  | SiO <sub>2</sub>               |             | 23,4 ± 0,1          | %    |        |        |