

Lead base, RM, Melting Point 327.3 Grad Celsius, Block 500 g (10.5 x 2 x 2 cms)

Art. ID BAS-BCS-RM 210E
Unit block
Deliverydetails No Dangerous Good /not restricted

| Text/Information | Analyte/Parameter | CAS number | Concentration/Value | Unit | Method | Source |
|------------------|-------------------|-------------|---------------------|------|--------|--------|
| | Silver (Ag) | [7440-22-4] | 0,0001 | % | | |
| | Aluminium (Al) | [7429-90-5] | <0,001 | % | | |
| | Bismuth (Bi) | [7440-69-9] | 0,0008 | % | | |
| | Copper (Cu) | [7440-50-8] | 0,0006 | % | | |
| | Iron (Fe) | [7439-89-6] | 0,0005 | % | | |
| | Manganese (Mn) | [7439-96-5] | <0,001 | % | | |
| | Nickel (Ni) | [7440-02-0] | <0,001 | % | | |
| | Lead (Pb) | [7439-92-1] | 99,996 | % | | |
| | Antimony (Sb) | [7440-36-0] | <0,002 | % | | |
| | Tin (Sn) | [7440-31-5] | <0,002 | % | | |
| | Titanium (Ti) | [7440-32-6] | 0,001 | % | | |
| | Zinc (Zn) | [7440-66-6] | <0,005 | % | | |