

## **Zircon, RM, Powder 100 g**

Art. ID                      BAS-BCS-RM 204A  
Unit                         100 g  
Deliverydetails            No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		0,5	%		
	Al <sub>2</sub> O <sub>3</sub>		0,74	%		
	CaO		0,15	%		
	Fe <sub>2</sub> O <sub>3</sub>		0,18	%		
	K <sub>2</sub> O		0,017	%		
	MgO	[1309-48-4]	0,012	%		
	Na <sub>2</sub> O		0,014	%		
	P <sub>2</sub> O <sub>5</sub>		0,77	%		
	SiO <sub>2</sub>		37,6	%		
	SnO <sub>2</sub>		1,69	%		
	TiO <sub>2</sub>		2,22	%		
	ZrO <sub>2</sub>		53,8 (incl HfO <sub>2</sub> )	%		