

**Cement, CRM, Powder 100 g**

Art. ID                      BAS-BCS-CRM 353  
Unit                         100 g  
Deliverydetails            No Dangerous Good /not restricted

| Text/Information | Analyte/Parameter              | CAS number  | Concentration/Value | Unit | Method | Source |
|------------------|--------------------------------|-------------|---------------------|------|--------|--------|
|                  | Al <sub>2</sub> O <sub>3</sub> |             | 3,77                | %    |        |        |
|                  | CaO                            |             | 64,8                | %    |        |        |
|                  | Fe <sub>2</sub> O <sub>3</sub> |             | 4,82                | %    |        |        |
|                  | K <sub>2</sub> O               |             | 0,49                | %    |        |        |
|                  | MgO                            | [1309-48-4] | 2,42                | %    |        |        |
|                  | Mn <sub>2</sub> O <sub>3</sub> |             | 0,23                | %    |        |        |
|                  | Na <sub>2</sub> O              |             | 0,1                 | %    |        |        |
|                  | P <sub>2</sub> O <sub>5</sub>  |             | 0,077               | %    |        |        |
|                  | SO <sub>3</sub>                |             | 2,25                | %    |        |        |
|                  | SiO <sub>2</sub>               |             | 20,5                | %    |        |        |
|                  | SrO                            |             | 0,23                | %    |        |        |
|                  | TiO <sub>2</sub>               |             | 0,16                | %    |        |        |