

Slag, CRM, Steelmaking Slag, Powder 100 g

Art. ID BAS-BCS-CRM 381
Unit 100 g
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al ₂ O ₃		0,67	%		
	CaO		49	%		
	Cr ₂ O ₃		0,33	%		
	Iron (Fe)	[7439-89-6]	13,3	%		
	FeO		3,69	%		
	MgO	[1309-48-4]	1,03	%		
	MnO		3,16	%		
	P ₂ O ₅		15,7 (tot)	%		
	P ₂ O ₅ soluble		15,2	%		
	Sulfur (S)	[7704-34-9]	0,19	%		
	SiO ₂		8,78	%		
	TiO ₂		0,35	%		
	V ₂ O ₅		0,94	%		