

Slag, CRM, Steelmaking Slag, Powder 100 g

Art. ID BAS-BCS-CRM 381
Unit 100 g
Deliverydetails No Dangerous Good /not restricted

| Text/Information | Analyte/Parameter | CAS number | Concentration/Value | Unit | Method | Source |
|------------------|---------------------------------------|-------------|---------------------|------|--------|--------|
| | Al ₂ O ₃ | | 0,67 | % | | |
| | CaO | | 49 | % | | |
| | Cr ₂ O ₃ | | 0,33 | % | | |
| | Iron (Fe) | [7439-89-6] | 13,3 | % | | |
| | FeO | | 3,69 | % | | |
| | MgO | [1309-48-4] | 1,03 | % | | |
| | MnO | | 3,16 | % | | |
| | P ₂ O ₅ | | 15,7 (tot) | % | | |
| | P ₂ O ₅ soluble | | 15,2 | % | | |
| | Sulfur (S) | [7704-34-9] | 0,19 | % | | |
| | SiO ₂ | | 8,78 | % | | |
| | TiO ₂ | | 0,35 | % | | |
| | V ₂ O ₅ | | 0,94 | % | | |