

**Bauxite, CRM, Powder 100 g**

Art. ID                      BAS-BCS-CRM 395  
Unit                         100 g  
Deliverydetails            No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		27,8	%		
	Al <sub>2</sub> O <sub>3</sub>		52,4	%		
	CaO		0,05	%		
	Cr <sub>2</sub> O <sub>3</sub>		~0,07	%		
	Fe <sub>2</sub> O <sub>3</sub>		16,3	%		
	MgO	[1309-48-4]	0,02	%		
	SiO <sub>2</sub>		1,24	%		
	TiO <sub>2</sub>		1,93	%		