

**Bauxite, CRM, Powder 100 g**

Art. ID                      BAS-BCS-CRM 395  
Unit                         100 g  
Deliverydetails            No Dangerous Good /not restricted

| Text/Information | Analyte/Parameter              | CAS number  | Concentration/Value | Unit | Method | Source |
|------------------|--------------------------------|-------------|---------------------|------|--------|--------|
|                  | Loss on Ignition (LOI)         |             | 27,8                | %    |        |        |
|                  | Al <sub>2</sub> O <sub>3</sub> |             | 52,4                | %    |        |        |
|                  | CaO                            |             | 0,05                | %    |        |        |
|                  | Cr <sub>2</sub> O <sub>3</sub> |             | ~0,07               | %    |        |        |
|                  | Fe <sub>2</sub> O <sub>3</sub> |             | 16,3                | %    |        |        |
|                  | MgO                            | [1309-48-4] | 0,02                | %    |        |        |
|                  | SiO <sub>2</sub>               |             | 1,24                | %    |        |        |
|                  | TiO <sub>2</sub>               |             | 1,93                | %    |        |        |