

Bauxite, CRM, Powder 100 g

Art. ID BAS-BCS-CRM 395
Unit 100 g
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		27,8	%		
	Al ₂ O ₃		52,4	%		
	CaO		0,05	%		
	Cr ₂ O ₃		~0,07	%		
	Fe ₂ O ₃		16,3	%		
	MgO	[1309-48-4]	0,02	%		
	SiO ₂		1,24	%		
	TiO ₂		1,93	%		