

Sand, CRM Glass Sand 11, Powder 100 g (SGT-S11)

Art. ID BAS-BCS-CRM 528
Unit 100 g
Deliverydetails No Dangerous Good /not restricted

| Text/Information | Analyte/Parameter | CAS number | Concentration/Value | Unit | Method | Source |
|------------------|--------------------------------|-------------|---------------------|------|--------|--------|
| | Loss on Ignition (LOI) | | 0,271 | % | | |
| | Al ₂ O ₃ | | 2,447 | % | | |
| | BaO | | 0,0298 | % | | |
| | CaO | | 0,237 | % | | |
| | Cr ₂ O ₃ | | 0,0008 | % | | |
| | Fe ₂ O ₃ | | 0,1111 | % | | |
| | K ₂ O | | 0,875 | % | | |
| | MgO | [1309-48-4] | 0,0887 | % | | |
| | Manganese (Mn) | [7439-96-5] | (<0,002) | % | | |
| | Na ₂ O | | 0,101 | % | | |
| | PbO | | 0,0006 | % | | |
| | SiO ₂ | | 95,62 | % | | |
| | TiO ₂ | | 0,0486 | % | | |