

Open Hearth Slag, Steelmaking Slag (CMSI-1744)

Art. ID NCS HC13805
Unit 50 g
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al ₂ O ₃		3,92	%		
	CaO		26,73	%		
	Iron (Fe)	[7439-89-6]	34,33	%		
	FeO		36,55	%		
	MgO	[1309-48-4]	12,15	%		
	MnO		2,01	%		
	P ₂ O ₅		0,87	%		
	Sulfur (S)	[7704-34-9]	0,107	%		
	SiO ₂		8,91	%		
	TiO ₂		0,32	%		