

### **Open Hearth Slag, Steelmaking Slag (CMSI-1744)**

Art. ID                      NCS HC13805  
Unit                         50 g  
Deliverydetails            No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al <sub>2</sub> O <sub>3</sub>		3,92	%		
	CaO		26,73	%		
	Iron (Fe)	[7439-89-6]	34,33	%		
	FeO		36,55	%		
	MgO	[1309-48-4]	12,15	%		
	MnO		2,01	%		
	P <sub>2</sub> O <sub>5</sub>		0,87	%		
	Sulfur (S)	[7704-34-9]	0,107	%		
	SiO <sub>2</sub>		8,91	%		
	TiO <sub>2</sub>		0,32	%		