

### Open Hearth Slag, Steelmaking Slag (CMSI-1744)

Art. ID                      NCS HC13805  
Unit                         50 g  
Deliverydetails            No Dangerous Good /not restricted

| Text/Information | Analyte/Parameter              | CAS number  | Concentration/Value | Unit | Method | Source |
|------------------|--------------------------------|-------------|---------------------|------|--------|--------|
|                  | Al <sub>2</sub> O <sub>3</sub> |             | 3,92                | %    |        |        |
|                  | CaO                            |             | 26,73               | %    |        |        |
|                  | Iron (Fe)                      | [7439-89-6] | 34,33               | %    |        |        |
|                  | FeO                            |             | 36,55               | %    |        |        |
|                  | MgO                            | [1309-48-4] | 12,15               | %    |        |        |
|                  | MnO                            |             | 2,01                | %    |        |        |
|                  | P <sub>2</sub> O <sub>5</sub>  |             | 0,87                | %    |        |        |
|                  | Sulfur (S)                     | [7704-34-9] | 0,107               | %    |        |        |
|                  | SiO <sub>2</sub>               |             | 8,91                | %    |        |        |
|                  | TiO <sub>2</sub>               |             | 0,32                | %    |        |        |