

Electric Furnace Slag

Art. ID NCS HC13806
Unit 50 g
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Total Fe		13,11	%		
	SiO ₂		21,35	%		
	Al ₂ O ₃		4,00	%		
	MnO		13,6	%		
	FeO		15,25	%		
	TiO ₂		0,18	%		
	MgO	[1309-48-4]	15,8	%		
	Total Ca		16,22	%		
	P ₂ O ₅		0,125	%		
	Fluorine (F)	[7782-41-4]	0,17	%		