

Australian Iron Ore

Art. ID RRM-Fe-117-1KG
Unit 1 kg
Deliverydetails No Dangerous Good /not restricted

Description

Elements and Oxides determined as follows: Multi-element Iron Ore Suite - XRF fused disc analysis /// Loss on Ignition - Thermo Gravimetric Analysis

| Text/Information | Analyte/Parameter | CAS number | Concentration/Value | Unit | Method | Source |
|--|--------------------------------|-------------|---------------------|------|--------|--------|
| Corrected for moisture according to ISO2596:2006 | Iron (Fe) | [7439-89-6] | 42,02 | % | | |
| Corrected for moisture according to ISO2596:2006 | Iron (Fe) calculated | | 42,09 | % | | |
| Corrected for moisture according to ISO2596:2006 | SiO ₂ | | 16,28 | % | | |
| Corrected for moisture according to ISO2596:2006 | Al ₂ O ₃ | | 11,39 | % | | |
| Corrected for moisture according to ISO2596:2006 | TiO ₂ | | 1,07 | % | | |
| Corrected for moisture according to ISO2596:2006 | CaO | | 0,155 | % | | |
| Corrected for moisture according to ISO2596:2006 | K ₂ O | | 0,041 | % | | |
| Corrected for moisture according to ISO2596:2006 | MgO | [1309-48-4] | 0,271 | % | | |
| Corrected for moisture according to ISO2596:2006 | Manganese (Mn) | [7439-96-5] | 0,447 | % | | |
| Corrected for moisture according to ISO2596:2006 | Phosphorus (P) | [7723-14-0] | 0,028 | % | | |

| | | | | | |
|----|--|--------------------------------------|-------------|-------|---|
| 06 | Corrected for moisture according to ISO2596:20 | Sulfur (S) | [7704-34-9] | 0,066 | % |
| 06 | Corrected for moisture according to ISO2596:20 | Loss on Ignition (L.O.I .) (371 °C) | | 6,95 | % |
| 06 | Corrected for moisture according to ISO2596:20 | Loss on Ignition (L.O.I .) (425 °C) | | 7,74 | % |
| 06 | Corrected for moisture according to ISO2596:20 | Loss on Ignition (L.O.I .) (650 °C) | | 9,23 | % |
| 06 | Corrected for moisture according to ISO2596:20 | Loss on Ignition (L.O.I .) (1000 °C) | | 9,62 | % |
| 06 | Corrected for moisture according to ISO2596:20 | Arsenic (As) | [7440-38-2] | 0,005 | % |
| 06 | Corrected for moisture according to ISO2596:20 | Chlorine (Cl) | [7782-50-5] | 0,009 | % |
| 06 | Corrected for moisture according to ISO2596:20 | Cobalt (Co) | [7440-48-4] | - | % |
| 06 | Corrected for moisture according to ISO2596:20 | Copper (Cu) | [7440-50-8] | 0,004 | % |
| 06 | Corrected for moisture according to ISO2596:20 | Lead (Pb) | [7439-92-1] | 0,005 | % |
| 06 | Corrected for moisture according to ISO2596:20 | Zinc (Zn) | [7440-66-6] | 0,002 | % |
| 06 | Corrected for moisture according to ISO2596:20 | Barium (Ba) | [7440-39-3] | 0,037 | % |
| 06 | Corrected for moisture | Chromium (Cr) | [7440-47-3] | 0,012 | % |

according to ISO2596:20

06

| | | | | |
|------------------------|-------------|-------------|-------|---|
| Corrected for moisture | Nickel (Ni) | [7440-02-0] | 0,006 | % |
|------------------------|-------------|-------------|-------|---|

according to ISO2596:20

06

| | | | | |
|------------------------|----------|-------------|---|---|
| Corrected for moisture | Tin (Sn) | [7440-31-5] | - | % |
|------------------------|----------|-------------|---|---|

according to ISO2596:20

06

| | | | | |
|------------------------|----------------|-------------|-------|---|
| Corrected for moisture | Strontium (Sr) | [7440-24-6] | 0,003 | % |
|------------------------|----------------|-------------|-------|---|

according to ISO2596:20

06

| | | | | |
|------------------------|--------------|-------------|-------|---|
| Corrected for moisture | Vanadium (V) | [7440-62-2] | 0,018 | % |
|------------------------|--------------|-------------|-------|---|

according to ISO2596:20

06

| | | | | |
|------------------------|----------------|-------------|-------|---|
| Corrected for moisture | Zirconium (Zr) | [7440-67-7] | 0,026 | % |
|------------------------|----------------|-------------|-------|---|

according to ISO2596:20

06

| | | | | |
|-------------------------|-----------|-------------|-------|---|
| Drying to constant mass | Iron (Fe) | [7439-89-6] | 41,81 | % |
|-------------------------|-----------|-------------|-------|---|

| | | | | |
|-------------------------|----------------------|--|-------|---|
| Drying to constant mass | Iron (Fe) calculated | | 41,86 | % |
|-------------------------|----------------------|--|-------|---|

| | | | | |
|-------------------------|------------------|--|-------|---|
| Drying to constant mass | SiO ₂ | | 16,17 | % |
|-------------------------|------------------|--|-------|---|

| | | | | |
|-------------------------|--------------------------------|--|-------|---|
| Drying to constant mass | Al ₂ O ₃ | | 11,22 | % |
|-------------------------|--------------------------------|--|-------|---|

| | | | | |
|-------------------------|------------------|--|------|---|
| Drying to constant mass | TiO ₂ | | 1,06 | % |
|-------------------------|------------------|--|------|---|

| | | | | |
|-------------------------|-----|--|-------|---|
| Drying to constant mass | CaO | | 0,150 | % |
|-------------------------|-----|--|-------|---|

| | | | | |
|-------------------------|------------------|--|-------|---|
| Drying to constant mass | K ₂ O | | 0,040 | % |
|-------------------------|------------------|--|-------|---|

| | | | | |
|-------------------------|-----|-------------|-------|---|
| Drying to constant mass | MgO | [1309-48-4] | 0,274 | % |
|-------------------------|-----|-------------|-------|---|

| | | | | |
|-------------------------|----------------|-------------|-------|---|
| Drying to constant mass | Manganese (Mn) | [7439-96-5] | 0,443 | % |
|-------------------------|----------------|-------------|-------|---|

| | | | | |
|-------------------------|----------------|-------------|-------|---|
| Drying to constant mass | Phosphorus (P) | [7723-14-0] | 0,028 | % |
|-------------------------|----------------|-------------|-------|---|

| | | | | |
|-------------------------|------------|-------------|-------|---|
| Drying to constant mass | Sulfur (S) | [7704-34-9] | 0,063 | % |
|-------------------------|------------|-------------|-------|---|

| | | | | |
|-------------------------|---------------------------------------|--|------|---|
| Drying to constant mass | Loss on Ignition (L.O.I) (371 °C) | | 7,38 | % |
|-------------------------|---------------------------------------|--|------|---|

| | | | | |
|-------------------------|---------------------------------------|--|------|---|
| Drying to constant mass | Loss on Ignition (L.O.I) (425 °C) | | 8,21 | % |
|-------------------------|---------------------------------------|--|------|---|

| | | | | |
|-------------------------|---------------------------------------|--|------|---|
| Drying to constant mass | Loss on Ignition (L.O.I) (650 °C) | | 9,65 | % |
|-------------------------|---------------------------------------|--|------|---|

| | | | | |
|-------------------------|--|--|------|---|
| Drying to constant mass | Loss on Ignition (L.O.I) (1000 °C) | | 10,2 | % |
|-------------------------|--|--|------|---|

| | | | | |
|-------------------------|--------------|-------------|-------|---|
| Drying to constant mass | Arsenic (As) | [7440-38-2] | 0,006 | % |
|-------------------------|--------------|-------------|-------|---|

| | | | | |
|-------------------------|---------------|-------------|-------|---|
| Drying to constant mass | Chlorine (Cl) | [7782-50-5] | 0,011 | % |
|-------------------------|---------------|-------------|-------|---|

| | | | | |
|-------------------------|----------------|-------------|-------|---|
| Drying to constant mass | Cobalt (Co) | [7440-48-4] | - | % |
| Drying to constant mass | Copper (Cu) | [7440-50-8] | 0,006 | % |
| Drying to constant mass | Lead (Pb) | [7439-92-1] | 0,005 | % |
| Drying to constant mass | Zinc (Zn) | [7440-66-6] | 0,002 | % |
| Drying to constant mass | Barium (Ba) | [7440-39-3] | 0,034 | % |
| Drying to constant mass | Chromium (Cr) | [7440-47-3] | 0,014 | % |
| Drying to constant mass | Nickel (Ni) | [7440-02-0] | 0,009 | % |
| Drying to constant mass | Tin (Sn) | [7440-31-5] | - | % |
| Drying to constant mass | Strontium (Sr) | [7440-24-6] | 0,002 | % |
| Drying to constant mass | Vanadium (V) | [7440-62-2] | 0,019 | % |
| Drying to constant mass | Zirconium (Zr) | [7440-67-7] | 0,026 | % |