

Portland Composite Cement (CEM II/B-M 32,5 R) - Particle Size, Blaine Specific Area

Art. ID TL-203BGa
 Unit 40 g
 Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
Mean value	Particle density		3,05	g/cm3	picnometer method	
Mean value	Specific Surface Area (Blaine)		4329	cm2/g	EN 196-6	
Mean/Analysis by laser diffraction/Equivalent size: 1,25 µm	Particle size		9	%	ISO 13320-1	
Mean/Analysis by laser diffraction/Equivalent size: 1,6 µm	Particle size		11	%	ISO 13320-1	
Mean/Analysis by laser diffraction/Equivalent size: 2 µm	Particle size		13,5	%	ISO 13320-1	
Mean/Analysis by laser diffraction/Equivalent size: 2,5 µm	Particle size		16,5	%	ISO 13320-1	
Mean/Analysis by laser diffraction/Equivalent size: 3,15 µm	Particle size		19,8	%	ISO 13320-1	
Mean/Analysis by laser diffraction/Equivalent size: 4 µm	Particle size		23,6	%	ISO 13320-1	
Mean/Analysis by laser diffraction/Equivalent size: 5 µm	Particle size		27,7	%	ISO 13320-1	
Mean/Analysis by laser diffraction/Equivalent size: 6,3 µm	Particle size		32,1	%	ISO 13320-1	
Mean/Analysis by laser diffraction/Equivalent size: 8 µm	Particle size		37,2	%	ISO 13320-1	

Mean/Analysis by laser	Particle size	42,7	%	ISO 13320-1
diffraction/Equivalent	size: 10 µm			
Mean/Analysis by laser	Particle size	48,7	%	ISO 13320-1
diffraction/Equivalent	size: 12,5 µm			
Mean/Analysis by laser	Particle size	55,9	%	ISO 13320-1
diffraction/Equivalent	size: 16 µm			
Mean/Analysis by laser	Particle size	63,3	%	ISO 13320-1
diffraction/Equivalent	size: 20 µm			
Mean/Analysis by laser	Particle size	70,7	%	ISO 13320-1
diffraction/Equivalent	size: 25 µm			
Mean/Analysis by laser	Particle size	78,6	%	ISO 13320-1
diffraction/Equivalent	size: 31,5 µm			
Mean/Analysis by laser	Particle size	85,9	%	ISO 13320-1
diffraction/Equivalent	size: 40 µm			
Mean/Analysis by laser	Particle size	91,8	%	ISO 13320-1
diffraction/Equivalent	size: 50 µm			
Mean/Analysis by laser	Particle size	96,2	%	ISO 13320-1
diffraction/Equivalent	size: 63 µm			
Mean/Analysis by laser	Particle size	98,4	%	ISO 13320-1
diffraction/Equivalent	size: 80 µm			
Mean/Analysis by laser	Particle size	99,4	%	ISO 13320-1
diffraction/Equivalent	size: 100 µm			
Mean/Analysis by laser	Particle size	99,8	%	ISO 13320-1
diffraction/Equivalent	size: 125 µm			
Mean/Analysis by laser	Particle size	100	%	ISO 13320-1
diffraction/Equivalent				

size: 160 µm

Mean/Equivalent size: 3	83,2	%	NF X11-640
-------------------------	------	---	------------

1,5 µm

Mean/Equivalent size: 4	89,9	%	NF X11-640
-------------------------	------	---	------------

0 µm

Mean/Equivalent size: 5	93,4	%	NF X11-640
-------------------------	------	---	------------

0 µm

Mean/Equivalent size: 6	96,7	%	NF X11-640
-------------------------	------	---	------------

3 µm

Mean/Equivalent size: 8	98,9	%	NF X11-640
-------------------------	------	---	------------

0 µm

Mean/Equivalent size: 1	99,3	%	NF X11-640
-------------------------	------	---	------------

00 µm

Mean/Equivalent size: 1	99,7	%	NF X11-640
-------------------------	------	---	------------

25 µm

Mean/Equivalent size: 1	100	%	NF X11-640
-------------------------	-----	---	------------

60 µm