

Pulp Iron Ore

Art. ID GEO-GIOP-123
Unit each
Deliverydetails No Dangerous Good /not restricted

| Text/Information | Analyte/Parameter | CAS number | Concentration/Value | Unit | Method | Source |
|------------------|------------------------------------|-------------|---------------------|------|--------|--------|
| | Iron (Fe) | [7439-89-6] | 12,04 | % | | |
| | Al ₂ O ₃ | | 25,5 | % | | |
| | SiO ₂ | | 36,33 | % | | |
| | Phosphorus (P) | [7723-14-0] | 0,048 | % | | |
| | TiO ₂ | | 1,75 | % | | |
| | Loss on Ignition (L.O.I) (1000 | | 9,7 | % | | |