

Pulp Iron Ore

Art. ID GEO-GIOP-135
Unit each
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Iron (Fe)	[7439-89-6]	53,5	%		
	Al ₂ O ₃		7,3	%		
	SiO ₂		9,63	%		
	Phosphorus (P)	[7723-14-0]	0,059	%		
	TiO ₂		0,47	%		
	Loss on Ignition (L.O.I) (1000		3,6	%		