

Pulp Iron Ore

Art. ID GEO-GIOP-135
Unit each
Deliverydetails No Dangerous Good /not restricted

| Text/Information | Analyte/Parameter | CAS number | Concentration/Value | Unit | Method | Source |
|------------------|------------------------------------|-------------|---------------------|------|--------|--------|
| | Iron (Fe) | [7439-89-6] | 53,5 | % | | |
| | Al ₂ O ₃ | | 7,3 | % | | |
| | SiO ₂ | | 9,63 | % | | |
| | Phosphorus (P) | [7723-14-0] | 0,059 | % | | |
| | TiO ₂ | | 0,47 | % | | |
| | Loss on Ignition (L.O.I) (1000 | | 3,6 | % | | |