

Blast Furnace-Slag, RM, Powder (< 0,125 mm)

Art. ID DH-SX32-26
Unit 100 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	CaO		41,95	%	X-Ray Fluorescence Spectrometry (XRF)	
	SiO ₂		35,92	%	X-Ray Fluorescence Spectrometry (XRF)	
	Iron (Fe)	[7439-89-6]	0,174	%	X-Ray Fluorescence Spectrometry (XRF)	
	Manganese (Mn)	[7439-96-5]	0,236	%	X-Ray Fluorescence Spectrometry (XRF)	
	P ₂ O ₅		0,005	%	X-Ray Fluorescence Spectrometry (XRF)	
	Sulfur (S)	[7704-34-9]	1,17	%	X-Ray Fluorescence Spectrometry (XRF), Combustion with IR-Detection	
	Al ₂ O ₃		13,01	%	X-Ray Fluorescence Spectrometry (XRF)	

MgO	[1309-48-4]	6,37	%	X-Ray Fluorescence Spectrometry (XRF)
TiO ₂		0,614	%	X-Ray Fluorescence Spectrometry (XRF)
Na ₂ O		0,265	%	Atomic Absorption Spectrometry
K ₂ O		0,407	%	X-Ray Fluorescence Spectrometry (XRF)
SrO		0,064	%	X-Ray Fluorescence Spectrometry (XRF)
BaO		0,093	%	X-Ray Fluorescence Spectrometry (XRF)
ZrO ₂		0,039	%	X-Ray Fluorescence Spectrometry (XRF)