

Slag, RM, Blast Furnace Slag, Typical Analysis, Powder

Art. ID DH-SX32-28
Unit 100 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al ₂ O ₃		11,93	%		
	BaO		0,097	%		
	CaO		35,66	%		
	Iron (Fe)	[7439-89-6]	0,332	%		
	K ₂ O		1,235	%		
	MgO	[1309-48-4]	8,56	%		
	Manganese (Mn)	[7439-96-5]	1,342	%		
	Na ₂ O		0,388	%		
	P ₂ O ₅		0,014	%		
	Sulfur (S)	[7704-34-9]	0,781	%		
	SiO ₂		38,69	%		
	SrO		0,062	%		
	TiO ₂		0,638	%		
	V ₂ O ₅		0,007	%		
	ZrO ₂		0,035	%		