

## **Slag, RM, Blast Furnace Slag, Typical Analysis, Powder**

Art. ID DH-SX32-28  
Unit 100 g (powder)  
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al <sub>2</sub> O <sub>3</sub>		11,93	%		
	BaO		0,097	%		
	CaO		35,66	%		
	Iron (Fe)	[7439-89-6]	0,332	%		
	K <sub>2</sub> O		1,235	%		
	MgO	[1309-48-4]	8,56	%		
	Manganese (Mn)	[7439-96-5]	1,342	%		
	Na <sub>2</sub> O		0,388	%		
	P <sub>2</sub> O <sub>5</sub>		0,014	%		
	Sulfur (S)	[7704-34-9]	0,781	%		
	SiO <sub>2</sub>		38,69	%		
	SrO		0,062	%		
	TiO <sub>2</sub>		0,638	%		
	V <sub>2</sub> O <sub>5</sub>		0,007	%		
	ZrO <sub>2</sub>		0,035	%		