

## **Slag, RM, Blast Furnace Slag, Typical Analysis, Powder**

Art. ID DH-SX32-32  
Unit 100 g (powder)  
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al <sub>2</sub> O <sub>3</sub>		11,81	%		
	BaO		0,087	%		
	CaO		36,59	%		
	Iron (Fe)	[7439-89-6]	0,417	%		
	K <sub>2</sub> O		1,228	%		
	MgO	[1309-48-4]	8,12	%		
	Manganese (Mn)	[7439-96-5]	0,671	%		
	Na <sub>2</sub> O		0,437	%		
	Sulfur (S)	[7704-34-9]	1,06	%		
	SiO <sub>2</sub>		39,03	%		
	SrO		0,076	%		
	TiO <sub>2</sub>		0,589	%		
	ZrO <sub>2</sub>		0,022	%		