

Slag, RM, Blast Furnace Slag, Typical Analysis, Powder

Art. ID DH-SX32-33
Unit 100 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al ₂ O ₃		11,53	%		
	BaO		0,082	%		
	CaO		36,3	%		
	Cr ₂ O ₃		0,021	%		
	Iron (Fe)	[7439-89-6]	1,72	%		
	K ₂ O		0,462	%		
	MgO	[1309-48-4]	5,27	%		
	Manganese (Mn)	[7439-96-5]	0,907	%		
	Na ₂ O		0,193	%		
	P ₂ O ₅		0,026	%		
	Sulfur (S)	[7704-34-9]	0,804	%		
	SiO ₂		41,53	%		
	SrO		0,047	%		
	TiO ₂		0,621	%		
	V ₂ O ₅		0,019	%		
	ZrO ₂		0,046	%		