

## Slag, RM, Blast Furnace Slag, Typical Analysis, Powder

Art. ID DH-SX32-33  
Unit 100 g (powder)  
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al <sub>2</sub> O <sub>3</sub>		11,53	%		
	BaO		0,082	%		
	CaO		36,3	%		
	Cr <sub>2</sub> O <sub>3</sub>		0,021	%		
	Iron (Fe)	[7439-89-6]	1,72	%		
	K <sub>2</sub> O		0,462	%		
	MgO	[1309-48-4]	5,27	%		
	Manganese (Mn)	[7439-96-5]	0,907	%		
	Na <sub>2</sub> O		0,193	%		
	P <sub>2</sub> O <sub>5</sub>		0,026	%		
	Sulfur (S)	[7704-34-9]	0,804	%		
	SiO <sub>2</sub>		41,53	%		
	SrO		0,047	%		
	TiO <sub>2</sub>		0,621	%		
	V <sub>2</sub> O <sub>5</sub>		0,019	%		
	ZrO <sub>2</sub>		0,046	%		