

Slag, RM, Blast Furnace Slag, Typical Analysis, Powder

Art. ID DH-SX32-34
Unit 100 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al ₂ O ₃		11,32	%		
	BaO		0,087	%		
	CaO		37,26	%		
	Cr ₂ O ₃		0,018	%		
	Iron (Fe)	[7439-89-6]	0,742	%		
	K ₂ O		0,89	%		
	MgO	[1309-48-4]	5,37	%		
	Manganese (Mn)	[7439-96-5]	0,971	%		
	Sulfur (S)	[7704-34-9]	0,9	%		
	SiO ₂		41,51	%		
	SrO		0,048	%		
	TiO ₂		0,618	%		
	V ₂ O ₅		0,016	%		