

## **Slag, RM, Blast Furnace Slag, Typical Analysis, Powder**

Art. ID DH-SX32-35  
Unit 100 g (powder)  
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al <sub>2</sub> O <sub>3</sub>		15,68	%		
	BaO		0,107	%		
	Calcium (Ca)	[7440-70-2]	24,55	%		
	CaO		34,35	%		
	Cr <sub>2</sub> O <sub>3</sub>		0,005	%		
	Iron (Fe)	[7439-89-6]	2,87	%		
	K <sub>2</sub> O		0,09	%		
	MgO	[1309-48-4]	6,289	%		
	Manganese (Mn)	[7439-96-5]	0,341	%		
	Na <sub>2</sub> O		0,103	%		
	P <sub>2</sub> O <sub>5</sub>		0,015	%		
	Sulfur (S)	[7704-34-9]	1,539	%		
	SiO <sub>2</sub>		39,33	%		
	SrO		0,072	%		
	TiO <sub>2</sub>		0,229	%		
	V <sub>2</sub> O <sub>5</sub>		0,004	%		
	ZrO <sub>2</sub>		0,064	%		