

Slag, RM, Blast Furnace Slag, Typical Analysis, Powder

Art. ID DH-SX32-35
Unit 100 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al ₂ O ₃		15,68	%		
	BaO		0,107	%		
	Calcium (Ca)	[7440-70-2]	24,55	%		
	CaO		34,35	%		
	Cr ₂ O ₃		0,005	%		
	Iron (Fe)	[7439-89-6]	2,87	%		
	K ₂ O		0,09	%		
	MgO	[1309-48-4]	6,289	%		
	Manganese (Mn)	[7439-96-5]	0,341	%		
	Na ₂ O		0,103	%		
	P ₂ O ₅		0,015	%		
	Sulfur (S)	[7704-34-9]	1,539	%		
	SiO ₂		39,33	%		
	SrO		0,072	%		
	TiO ₂		0,229	%		
	V ₂ O ₅		0,004	%		
	ZrO ₂		0,064	%		