

Sand, RM, For Sliding Gates, Typical Analysis, Powder

Art. ID DH-SX45-02
Unit 100 g (powder)
Deliverydetails No Dangerous Good /not restricted

| Text/Information | Analyte/Parameter | CAS number | Concentration/Value | Unit | Method | Source |
|------------------|--------------------------------|-------------|---------------------|------|--------|--------|
| | Water Loss | | 0,177 | % | | |
| | Al ₂ O ₃ | | 5,69 | % | | |
| | Carbon (C) | [7440-44-0] | 0,471 (tot) | % | | |
| | CaO | | 0,038 | % | | |
| | Cr ₂ O ₃ | | 14,75 | % | | |
| | Iron (Fe) | [7439-89-6] | 6,31 (tot) | % | | |
| | K ₂ O | | 0,693 | % | | |
| | MgO | [1309-48-4] | 3,24 | % | | |
| | Mn ₃ O ₄ | | 0,074 | % | | |
| | Na ₂ O | | 0,062 | % | | |
| | NiO | | 0,033 | % | | |
| | P ₂ O ₅ | | 0,007 | % | | |
| | SiO ₂ | | 65,97 | % | | |
| | TiO ₂ | | 0,203 | % | | |
| | V ₂ O ₅ | | 0,11 | % | | |