

Continuous Casting Powder, RM, Typical Analysis, Powder

Art. ID DH-SX28-02
Unit 100 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al ₂ O ₃		3,09	%		
	Calcium (Ca)	[7440-70-2]	25,15	%		
	Fluorine (F)	[7782-41-4]	0,074	%		
	Fe ₂ O ₃		0,488	%		
	K ₂ O		0,83	%		
	MgO	[1309-48-4]	0,981	%		
	MnO		0,03	%		
	Na ₂ O		1,097	%		
	P ₂ O ₅		0,06	%		
	Sulfur (S)	[7704-34-9]	0,132	%		
	SiO ₂		57,5	%		
	SrO		0,02	%		
	TiO ₂		0,055	%		
	ZnO		0,004	%		