

Blast Furnace Slag

Art. ID NCS HC11801
Unit 60 g
Deliverydetails No Dangerous Good /not restricted

| Text/Information | Analyte/Parameter | CAS number | Concentration/Value | Unit | Method | Source |
|------------------|--------------------------------|-------------|---------------------|------|--------|--------|
| | SiO ₂ | | 34,31 | % | | |
| | MnO | | 0,34 | % | | |
| | P ₂ O ₅ | | 0,012 | % | | |
| | S | | 0,97 | % | | |
| | TiO ₂ | | 1,52 | % | | |
| | CaO | | 39,02 | % | | |
| | MgO | [1309-48-4] | 8,12 | % | | |
| | K ₂ O | | 0,47 | % | | |
| | Na ₂ O | | 0,41 | % | | |
| | Al ₂ O ₃ | | 13,83 | % | | |
| TFE | Fe total | | 0,411 | % | | |
| | Fluorine (F) | [7782-41-4] | ~0,062 | % | | |