

Ferro-Alloy, Mn 18.37% Fe 0.634% Sakura Ferro-Alloy MY

Art. ID AMIS-0533
Unit 1 kg
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al ₂ O ₃		6,97	%		
	Aluminium (Al)	[7429-90-5]	37030	ppm		
	Aluminium (Al)	[7429-90-5]	3,703	%		
	BaO		1,63	%		
	Barium (Ba)	[7440-39-3]	14461	ppm		
	Barium (Ba)	[7440-39-3]	1,4461	%		
	Calcium (Ca)	[7440-70-2]	19,09	%		
	CaO		26,59	%		
	Carbon (C)	[7440-44-0]	0,5	%		
	Chromium (Cr)	[7440-47-3]	812	ppm		
	Chromium (Cr)	[7440-47-3]	0,0812	%		
	Cr ₂ O ₃		0,12	%		
	Fe ₂ O ₃		0,91	%		
	Iron (Fe)	[7439-89-6]	0,63	%		
	K ₂ O		0,65	%		
	Magnesium (Mg)	[7439-95-4]	38000	ppm		
	Magnesium (Mg)	[7439-95-4]	3,8	%		
	Manganese (Mn)	[7439-96-5]	183700	ppm		
	Manganese (Mn)	[7439-96-5]	18,37	%		
	MgO	[1309-48-4]	6,43	%		
	MnO		23,97	%		
	Na ₂ O		0,42	%		
	Phosphorus (P)	[7723-14-0]	63	ppm		
	Phosphorus (P)	[7723-14-0]	0,0063	%		
	Silicon (Si)	[7440-21-3]	14,1	%		
	SiO ₂		29,85	%		
	Sulfur (S)	[7704-34-9]	0,83	%		
	TiO ₂		0,34	%		
	Titanium (Ti)	[7440-32-6]	0,2	%		
	Tungsten (W)	[7440-33-7]	3,5	ppm		
	Tungsten (W)	[7440-33-7]	0,00035	%		

