

Ferro-Alloy, Mn 20.2% Fe 1.20% Sakura Ferro-Alloy MY

Art. ID AMIS-0536
Unit 1 kg
Deliverydetails No Dangerous Good /not restricted

| Text/Information | Analyte/Parameter | CAS number | Concentration/Value | Unit | Method | Source |
|------------------|--------------------------------|-------------|---------------------|------|--------|--------|
| | Al ₂ O ₃ | | 8,17 | % | | |
| | Aluminium (Al) | [7429-90-5] | 43300 | ppm | | |
| | Aluminium (Al) | [7429-90-5] | 4,33 | % | | |
| | BaO | | 1,72 | % | | |
| | CaO | | 27,4 | % | | |
| | Carbon (C) | [7440-44-0] | 0,89 | % | | |
| | Chromium (Cr) | [7440-47-3] | 435 | ppm | | |
| | Chromium (Cr) | [7440-47-3] | 0,0435 | % | | |
| | Cr ₂ O ₃ | | 0,06 | % | | |
| | Fe ₂ O ₃ | | 1,71 | % | | |
| | Iron (Fe) | [7439-89-6] | 1,2 | % | | |
| | K ₂ O | | 0,61 | % | | |
| | Magnesium (Mg) | [7439-95-4] | 32200 | ppm | | |
| | Magnesium (Mg) | [7439-95-4] | 3,22 | % | | |
| | Manganese (Mn) | [7439-96-5] | 202000 | ppm | | |
| | Manganese (Mn) | [7439-96-5] | 20,2 | % | | |
| | MgO | [1309-48-4] | 5,27 | % | | |
| | MnO | | 26,3 | % | | |
| | SiO ₂ | | 26 | % | | |
| | Sulfur (S) | [7704-34-9] | 0,85 | % | | |
| | TiO ₂ | | 0,35 | % | | |
| | Titanium (Ti) | [7440-32-6] | 0,21 | % | | |
| | Tungsten (W) | [7440-33-7] | 2,4 | ppm | | |
| | Tungsten (W) | [7440-33-7] | 0,00024 | % | | |