

## **Ferro-Alloy, Mn 20.2% Fe 1.20% Sakura Ferro-Alloy MY**

Art. ID AMIS-0536  
Unit 1 kg  
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al <sub>2</sub> O <sub>3</sub>		8,17	%		
	Aluminium (Al)	[7429-90-5]	43300	ppm		
	Aluminium (Al)	[7429-90-5]	4,33	%		
	BaO		1,72	%		
	CaO		27,4	%		
	Carbon (C)	[7440-44-0]	0,89	%		
	Chromium (Cr)	[7440-47-3]	435	ppm		
	Chromium (Cr)	[7440-47-3]	0,0435	%		
	Cr <sub>2</sub> O <sub>3</sub>		0,06	%		
	Fe <sub>2</sub> O <sub>3</sub>		1,71	%		
	Iron (Fe)	[7439-89-6]	1,2	%		
	K <sub>2</sub> O		0,61	%		
	Magnesium (Mg)	[7439-95-4]	32200	ppm		
	Magnesium (Mg)	[7439-95-4]	3,22	%		
	Manganese (Mn)	[7439-96-5]	202000	ppm		
	Manganese (Mn)	[7439-96-5]	20,2	%		
	MgO	[1309-48-4]	5,27	%		
	MnO		26,3	%		
	SiO <sub>2</sub>		26	%		
	Sulfur (S)	[7704-34-9]	0,85	%		
	TiO <sub>2</sub>		0,35	%		
	Titanium (Ti)	[7440-32-6]	0,21	%		
	Tungsten (W)	[7440-33-7]	2,4	ppm		
	Tungsten (W)	[7440-33-7]	0,00024	%		