

Low Iron Sand, CRM, Glass Sand, Powder 100 g

Art. ID BAS-BCS-CRM 531
Unit 100 g
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al ₂ O ₃		0,0327	%		
	BaO		0,00112	%		
	CaO		0,004	%		
	Fe ₂ O ₃		0,00636	%		
	K ₂ O		0,0039	%		
	MgO	[1309-48-4]	0,00132	%		
	MnO		0,00014	%		
	P ₂ O ₅		0,00082	%		
	SiO ₂		99,74	%		
	SrO		0,00017	%		
	TiO ₂		0,016	%		