

Low Iron Sand, CRM, Glass Sand, Powder 100 g

Art. ID BAS-BCS-CRM 531
Unit 100 g
Deliverydetails No Dangerous Good /not restricted

| Text/Information | Analyte/Parameter | CAS number | Concentration/Value | Unit | Method | Source |
|------------------|--------------------------------|-------------|---------------------|------|--------|--------|
| | Al ₂ O ₃ | | 0,0327 | % | | |
| | BaO | | 0,00112 | % | | |
| | CaO | | 0,004 | % | | |
| | Fe ₂ O ₃ | | 0,00636 | % | | |
| | K ₂ O | | 0,0039 | % | | |
| | MgO | [1309-48-4] | 0,00132 | % | | |
| | MnO | | 0,00014 | % | | |
| | P ₂ O ₅ | | 0,00082 | % | | |
| | SiO ₂ | | 99,74 | % | | |
| | SrO | | 0,00017 | % | | |
| | TiO ₂ | | 0,016 | % | | |