

Continuous Casting mold powder

Art. ID NCS HC26802
Unit 50 g
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	SiO ₂		23,08	%		
	Calcium (Ca) total		17,93	%		
	Na ₂ O		2,94	%		
	Al ₂ O ₃		14,14	%		
	MgO	[1309-48-4]	5,86	%		
	Free Carbon		9,94	%		
	Total carbon		12,71	%		
	Fluorine (F)	[7782-41-4]	~3,86	%		