

Continuous Casting mold powder

Art. ID NCS HC26804
Unit 50 g
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	SiO ₂		34,95	%		
	Calcium (Ca) total		19,13	%		
	Na ₂ O		4,99	%		
	Al ₂ O ₃		5,3	%		
	MgO	[1309-48-4]	0,78	%		
	Free Carbon		14,49	%		
	Total carbon		15,86	%		
	Fluorine (F)	[7782-41-4]	~5,15	%		