

## Continuous Casting mold powder

Art. ID                      NCS HC26805  
Unit                         50 g  
Deliverydetails            No Dangerous Good /not restricted

| Text/Information | Analyte/Parameter              | CAS number  | Concentration/Value | Unit | Method | Source |
|------------------|--------------------------------|-------------|---------------------|------|--------|--------|
|                  | SiO <sub>2</sub>               |             | 41,31               | %    |        |        |
|                  | Calcium (Ca) total             |             | 21,46               | %    |        |        |
|                  | Na <sub>2</sub> O              |             | 4,07                | %    |        |        |
|                  | Al <sub>2</sub> O <sub>3</sub> |             | 6,93                | %    |        |        |
|                  | MgO                            | [1309-48-4] | 3,26                | %    |        |        |
|                  | Free Carbon                    |             | 1,57                | %    |        |        |
|                  | Total carbon                   |             | 3,06                | %    |        |        |
|                  | Fluorine (F)                   | [7782-41-4] | ~4,79               | %    |        |        |