

Bauxite

Art. ID NCS HC28814
Unit 50 g
Deliverydetails No Dangerous Good /not restricted

| Text/Information | Analyte/Parameter | CAS number | Concentration/Value | Unit | Method | Source |
|------------------|--------------------------------|-------------|---------------------|------|--------|--------|
| | Al ₂ O ₃ | | 83,07 | % | | |
| | CaO | | 0,22 | % | | |
| | MgO | [1309-48-4] | 0,088 | % | | |
| | P ₂ O ₅ | | 0,18 | % | | |
| | Fe ₂ O ₃ | | 2,71 | % | | |
| | TiO ₂ | | 3,64 | % | | |
| | MnO | | 0,011 | % | | |
| | SiO ₂ | | 9,69 | % | | |
| | K ₂ O | | 0,17 | % | | |
| | Na ₂ O | | 0,022 | % | | |
| | Loss on Ignition (LOI) | | 0,15 | % | | |
| | Carbon (C) | [7440-44-0] | 0,05 | % | | |